

CXE-206 Liner

Technical Data Sheet CXE-206

FOR PROFESSIONAL USE ONLY

This product is intended for use by professional installers. For best project results read all the applicable product information including MSDS, Technical Data Sheet and Product Specification Sheet before using this product.

Product Description

CXE-206 is a three component, 100% solids, trowelable epoxy liner system.

Product Application

Smooths out Pitted Walls.
Excellent for Filling Concrete Block.
Protection to Trenches, Pits, Sumps, Manholes and Concrete Pipes.

Benefits

Solvent Free, Low Odor, VOC Compliant
U.S.D.A. Compliant
Good Chemical Resistance
Can Be Applied up to 1/8" Thick in One Pass
Can Be Reinforced with Fiberglass
Excellent Impact and Abrasion Resistance
Resin-Rich
Easy to Clean Hygienic Surface

Packaging/Coverage

1 Gallon Kit = 12.8 SF @ 1/8"
3 Gallon Kit – 38.4 SF @ 1/8"
Also available in Bulk Kits

Surface Preparation

Proper surface preparation is critical. The area should be cleaned of all oil, grease, etc. and be mechanically prepared by shot blasting, grinding, or scarifying.

Mixing Directions

Mix Part A and Part B together with a Jiffy blade for approximately thirty seconds. Be careful not to introduce excess air into the material. Add Part C (filler) and mix for approximately one minute. Make sure bottom and sides of bucket are scraped to ensure complete mixing.

Application Instructions

Apply the material onto the wall with a trowel to the manufacturer's recommended coverage.

Cure Times at 72°F

Regular Cure

Pot Life	40 – 45 minutes
Re-Coat	15 Hours
Foot Traffic	15 Hours
Forklift Traffic	48 Hours
Full Chemical Resistance	7 Days

Fast Cure

Pot Life	20 – 25 minutes
Re-Coat	4 Hours
Foot Traffic	4 Hours
Forklift Traffic	24 Hours
Full Chemical Resistance	7 Days

Priming

CXE-206 is resin-rich and does not need a primer on sound concrete, however, to help reduce outgassing, blistering and dry spots, we recommend first priming with CXE-200 or the CXE-600 Primer.

Colors

Available in Gray, Dark Gray, Red and White. Special colors available upon request.

Storage/Shelf Life

Materials should be stored at 50°F – 90°F and out of direct sunlight. Shelf life is one year in unopened containers.

Safety

Please read MSDS before using this product.

Cleanup

Clean mixing and application tools immediately with warm soapy water.

CXE-206 Liner

Technical Data Sheet CXE-206

Physical Properties

Mixing Ratio by Volume

Part A to Part B: 2:1

A & B Mixed to Filler: 1 to 2

Coverage per Gallon

12.8 SF @ 1/8"

Limitations/Precautions

During installation and initial cure, substrate and air temperature must be at least 40°F.

Warranty

Corvixx Polymers Corporation warrants our products to be free of manufacturing defects. Liability for products proven defective is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Corvixx Polymers Corporation. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CORVIXX POLYMERS CORPORATION, EXPRESSED OR IMPLIED.